



สีรองพื้นปูนใหม่ซูเปอร์คอก ผลิตจากสารอะครีลิกที่มีความทนทานต่อฤทธิ์ต่างซึ่งเป็นตัวละลายฟิล์มสีที่มีอยู่ในผนังปูนได้ดี เหมาะสำหรับใช้สำหรับทาภายนอกและภายใน อีกทั้งยังช่วยเสริมการยึดเกาะของสีทับหน้ากับผนัง ทำให้ไม่เกิดรอยต่าง และมีประสิทธิภาพในการต่อต้านเชื้อราได้ดีเยี่ยม ไม่ผสมสารตะกั่วและปรอท

ข้อมูลทางเทคนิคและคุณสมบัติของฟิล์มสี

ประเภทสี	สีรองพื้นปูน อะครีลิก
ลักษณะฟิล์มสี	ด้าน
ขนาดบรรจุ	1 และ 5 ยูเอสแกลลอน
เฉดสี	สีขาวอมฟ้า
เนื้อสีโดยปริมาตร	30 - 40%
ระยะเวลาแห้งสัมผัส	ไม่น้อยกว่า 30 นาที
ระยะเวลาทาทับ	อย่างน้อย 30 นาที - 2 ชั่วโมง
การครอบคลุมพื้นที่ตามทฤษฎี	35 - 40 ตร.ม. / เที่ยว / แกลลอน
*พื้นที่ครอบคลุมเป็นค่าทางทฤษฎี อาจแตกต่างจากการใช้งานจริงไม่เกิน 20%	

วิธีการใช้งาน

วิธีการใช้งาน	แปรง ลูกกลิ้ง หรือสเปรย์
การผสมก่อนใช้งาน	ใช้ได้ทันที หรือหากต้องการผสม ให้เติมน้ำสะอาด 1 ส่วนต่อสี 10 ส่วน (10%)
การทำความสะอาด	ล้างทำความสะอาดอุปกรณ์ด้วยน้ำเปล่าทันทีหลังการใช้งาน

ระบบการทาสี

ก่อนการทาสีทุกครั้ง พื้นผิวจะต้องแห้ง สะอาด ปราศจากฝุ่นละออง เศษซีเมนต์ คราบไขมัน และสิ่งสกปรกต่างๆ หากมีรอยแตกร้าวกว้างไม่เกิน 1 มม. ให้ซ่อมด้วยสีโป๊วซูเปอร์คอก อะครีลิก (A952-400) ชัดแต่งให้เรียบและให้แน่ใจว่าผนังไม่มีรอยรั่วซึมของน้ำ เพื่อป้องกันฟิล์มสีโป่งพองภายหลัง

ขั้นที่ 1 การเตรียมพื้นผิว

- พื้นผิวปูนใหม่ไม่เคยทาสี หรือทาสีแล้วสียังอยู่ในสภาพดี ทั้งพื้นผิวปูนแห้งสนิทอย่างน้อย 1 เดือน หลังจากฉาบปูน มีความชื้นไม่เกิน 14%

ขั้นที่ 2 การทาสีรองพื้น

- พื้นผิวปูนใหม่ไม่เคยทาสี หรือทาสีแล้วสียังอยู่ในสภาพดี ทาสีรองพื้นปูนใหม่ซูเปอร์คอก A917-800 จำนวน 1 เที่ยว ทั้งให้แห้งอย่างน้อย 30 นาที - 2 ชั่วโมง ก่อนทาสีทับหน้า

ขั้นที่ 3 การทาสีทับหน้า

ทาสีทับหน้าด้วยสีน้ำอะครีลิกชนิดใดก็ได้ในตระกูล ซูเปอร์คอก อย่างน้อย 2 เที่ยว โดยทิ้งระยะห่างระหว่างสีที่ทาล้างแรกและชั้นถัดไป ประมาณ 30 นาที - 2 ชั่วโมง



Supercote Acrylic Alkali Resisting Primer

Acrylic primer for exterior and interior



Supercote Acrylic Alkali Resisting Primer made from a high quality waterborne acrylic primer and suitable for interior and exterior application. To enhance the adhesive between subsequent and top-coat. Resistant to fungus attack, no added lead and mercury.

Technical Information & Paint Film Properties

Type of Paint	Acrylic alkali resistance masonry primer
Finish	Matt
Pack size	1 and 5 U.S.Gallons
Colour Offer	Bluish white
Volume Solids	30 - 40%
Touch Dry	At least 30 minutes
Recoat Dry	At least 30 minutes – 2 hours
Theoretical Coverage	35 – 40 Sq.m./Coat/U.S.Gallon

*Coverage is theoretical value and may differ from real application +20%

Application

Application Method	Brush, Roller or Spray
Mixing Ratio	Ready for use. Or add up to 1 part clean water to 10 parts of paint (10%), if need
Cleaning Up	Clean all equipment with clean water immediately after use

Application System

Before painting every time, the surface must be cleaned until free from dirt and grease. If any, repair small cracks smaller than 1mm with Supercote Wall Putty. Rub down and make sure no cracks appeared for any possible water leakage in order to prevent paint film blistering later on.

Step 1: Surface Preparation

- *New masonry or previously painted in good condition* Leave new masonry to be fully cured at least 1 month. Moisture not over 14%. Allow surfaces to dry out.

Step 2: Priming

- *New masonry or previously painted in good condition* Apply 1 coat of Supercote Acrylic Alkali Resisting Primer A917-800. Allow at least 30 minutes - 2 hours to dry before applying topcoat.

Step 3: Topcoat

Apply at least 2 coats of Supercote Acrylic Paints. Allow at least 30 minutes - 2 hours drying between coats.



มท. 1123-2555
สีรองพื้นสำหรับงานปูน



TGL-4-R4-14



GREENLY DERIVED



ISO 9001 QMS03026/630
ISO 14001 EMS05021/198
OHSAS 18001 OHSAS04016/079
TIS 18001 OHS01013/028

The information in this datasheet is given to the best of our knowledge based on laboratory testing and for use recommendation. As the product is often used under conditions beyond our control, the company cannot guarantee anything only the quality of the product.

AkzoNobel Paints (Thailand) Ltd. (Former ICI Points (Thailand) Ltd.) 34/5 Moo 1 Choeng Watana Road, Klongklue, Pakkred Nonthaburi 11120
Customer Service : Telephone (662) 572-8888 Fax (662) 572-8889, www.dulux.co.th, www.facebook.com/duluxthailand